

**Sequel 2430**

TPE-MX

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>20</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	<b>24</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>2100</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>42</b>	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	<b>110</b>	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	<b>1040</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America

**Special Characteristics**

High impact or impact modified