

Product Texts

Available in natural and black colors.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	5	g/10min	ISO 1133
Temperature	190	°C	-
Load	5	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Tensile Strength	5.8	MPa	ISO 527
Strain at break	785	%	ISO 527
Shore A hardness	60	-	ISO 7619-1

Thermal properties

	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	110	°C	ISO 11357-1/-3

Other properties

	Value	Unit	Test Standard
Density	1180	kg/m ³	ISO 1183

Processing Recommendation Extrusion

	Value	Unit	Test Standard
Melt temperature	190	°C	-

Characteristics

Processing

Other Extrusion

Special Characteristics

Light stabilized or stable to light

Features

Thermal Stability, Copolymer

Chemical Resistance

General Chemical Resistance, Solvent Resistance, Ozone Resistance

Regional Availability

Europe