

Polywood A3 25 TPE 20006

TPE-W25

Grade is obsolete.

Advanced Compounding GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	350	MPa	ISO 527
Tensile Strength	7.7	MPa	ISO 527
Strain at break	32	%	ISO 527
Charpy notched impact strength, +23°C	24	kJ/m ²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	940	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Certifications

Contains renewable resources

Delivery form

Pellets

Regional Availability

Europe