

LOTTMER SE-130AN

TPE

Lotte Chemical Corporation

| Mechanical properties | Value | Unit | Test Standard |
|--------------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Modulus at 100% Elongation | 1.2 | MPa | ASTM D 412 |
| Shore A Hardness | 30 | - | ASTM D 2240 |
| Tear Strength | 13 | kN/m | ASTM D 624 |
| Izod Impact notched, Low-Temperature | N | J/m | ASTM D 256 |
| Temperature | -40 | °C | - |
| Tensile Strength at Break | 4.4 | MPa | ASTM D 412 |
| Elongation at Break | 850 | % | ASTM D 412 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 900 | kg/m ³ | ASTM D 792 |

Characteristics**Special Characteristics**

U.V. stabilized or stable to weather

Regional Availability

North America, Europe, Asia Pacific

Chemical Resistance

Ozone Resistance