

**Maxprene MX35AS001NC001**

TPE

Plásticos Novacor Ltda

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>7</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>1.7</b>	MPa	ASTM D 638
Shore A Hardness	<b>35</b>	-	ASTM D 2240

**Characteristics****Processing**

Injection Molding

**Regional Availability**

South and Central America