

Maxprene MX78AS001NC001

TPE

Plásticos Novacor Ltda

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	6.5	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	6.5	MPa	ASTM D 638
Shore A Hardness	78	-	ASTM D 2240

Characteristics**Processing**

Injection Molding

Regional Availability

South and Central America