

## Maxprene MX92AS001CZ021

TPE

Plásticos Novacor Ltda

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Shore A Hardness	92.5	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	105	°C	ASTM D 648
DTUL @ 264 psi	60	°C	ASTM D 648
Vicat Temperature	140	°C	ASTM D 1525

### Characteristics

#### Processing

Injection Molding

#### Regional Availability

South and Central America