

P3930CT

TPE

Nantong Polymax Elastomer Technology Co., Ltd.

Product Texts

For more detailed information, please read our [brochure](#) or contact our representatives in your region.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|--------------|-------|---------------|
| ASTM Data | | | |
| Mold Shrinkage, MD | 0.022 | mm/mm | ASTM D 955 |

| Mechanical properties | Value | Unit | Test Standard |
|----------------------------|-------------|------|---------------|
| ASTM Data | | | |
| Modulus at 100% Elongation | 1.05 | MPa | ASTM D 412 |
| Modulus at 300% Elongation | 2.14 | MPa | ASTM D 412 |
| Shore A Hardness | 32 | - | ASTM D 2240 |

| Other properties | Value | Unit | Test Standard |
|------------------|------------|-------------------|---------------|
| Density | 890 | kg/m ³ | ASTM D 792 |

Characteristics

Regional Availability

North America, Asia Pacific