

PELPRENE™ P40BU

TPE

Toyobo Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	190	°C	-
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	16	MPa	ASTM D 638
Flexural Modulus	23	MPa	ASTM D 790
Shore D Hardness	31	-	ASTM D 2240
Tear Strength	76	kN/m	ASTM D 624
Taber Abrasion Resistance	20	mg/1000 cycles	ASTM D 1044
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Coefficient of Thermal Expansion, MD	200	E-6/K	ASTM D 696
Melting Temperature	180	°C	ASTM D 3418
Vicat Temperature	89	°C	ASTM D 1525
Electrical properties			
ASTM Data			
Volume Resistivity	1E12	Ohm*cm	ASTM D 257
Other properties			
Density	1070	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	100 - 120	°C	-
Pre-drying - Time	4	h	-

Characteristics**Delivery form**

Pellets

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

U.V. stabilized or stable to weather