

POLYelast TPE EDS80 D35

TPE

Polykemi AB

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Charpy notched impact strength, +23°C	25	kJ/m ²	ISO 179/1eA
ASTM Data			
Shore D Hardness	35	-	ASTM D 2240
Other properties			
Density	910	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific

Delivery form

Granules