

## Prime Tuff TX 301

TPE

Primex Color, Compounding & Additives

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	0.8	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	20.8	MPa	ASTM D 638
Flexural Modulus	2096	MPa	ASTM D 790
Izod Impact notched, 1/8 in	1040	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1080	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Thermoforming

#### Features

Good Adhesion

#### Chemical Resistance

General Chemical Resistance

#### Applications

Automotive, Electrical and Electronical

#### Regional Availability

North America