

RESIPRENE® 1030

TPE

Resirene

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	14	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	5	kg	-
Mechanical properties			
ISO Data			
Shore A hardness	30	-	ISO 7619-1
ASTM Data			
Tensile Strength at Break	1.73	MPa	ASTM D 638
Elongation at Break	1500	%	ASTM D 638
Other properties			
Density	1070	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

South and Central America

Features

Soft Feel