

**RESIPRENE® 3075**

TPE

Resirene

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>12</b>	g/10min	ASTM D 1238
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Shore A hardness	<b>75</b>	-	ISO 7619-1
<b>ASTM Data</b>			
Tensile Strength at Break	<b>5</b>	MPa	ASTM D 638
Elongation at Break	<b>1000</b>	%	ASTM D 638
<b>Other properties</b>			
Density	<b>1100</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Applications**

Automotive

**Features**

Soft Feel

**Regional Availability**

South and Central America