

**Product Texts**

Styrenic block copolymer (SEPS)

Styrene content: 30%

The SEPS structure generates high elongation properties as well as enhanced low temperature properties without crystallization. With its broad range of hardnesses, it is used in various applications like personal care, medical, automotive, impact modification, film and adhesives.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>[5]</sup></b>			
Melt flow index, MFI	<b>70</b>	g/10min	
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

S: These properties are reported by the producer according standards that are different to our defaults.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>[5]</sup></b>			
Shore A hardness	<b>80</b>	-	

S: These properties are reported by the producer according standards that are different to our defaults.

**Characteristics**

**Delivery form**

Pellets

**Applications**

Automotive, Medical

**Features**

Good Adhesion, Copolymer

**Regional Availability**

North America, Europe, Asia Pacific