

Septon™ 8007L

TPE

Kuraray Co., Ltd.

Product Texts

Styrenic block copolymer (SEBS)

Styrene content: 30%

With its popular mid-block structure as an industry standard material, SEPTON™ 8000-series is an excellent choice, and Kuraray's customers use SEPTON™ 8000-series in adhesives, automotive, and personal care products.

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[5]			
Melt flow index, MFI	0.3	g/10min	
Temperature	230	°C	-
Load	2.16	kg	-

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
Other Standards^[5]			
Shore A hardness	77	-	

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Delivery form

Pellets

Applications

Automotive

Features

Good Adhesion, Copolymer, Random Copolymer

Regional Availability

North America, Europe, Asia Pacific