

Softflex® 6001

TPE

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.017	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.017	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Shore A Hardness	65	-	ASTM D 2240
Compression Set , 22 hr @ 73 °F	30	%	ASTM D 395
Other properties			
Density	910	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion, Blow Molding

Regional Availability

North America

Chemical Resistance

General Chemical Resistance