

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	235	°C	-
Load	1	kg	-
Mold Shrinkage, MD	0.017	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.015	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	72	-	ASTM D 2240
Tear Strength	40.3	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	896	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America