

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Modulus at 300% Elongation	7.18	MPa	ASTM D 412
Shore A Hardness	94	-	ASTM D 2240
Tear Strength	50.9	kN/m	ASTM D 624
Tensile Strength	12.4	MPa	ASTM D 412
Elongation at Break	610	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1150	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Delivery form

Natural Color

### Special Characteristics

U.V. stabilized or stable to weather

### Features

Good Adhesion

### Certifications

Food contact, Food approval FDA 21 CFR

### Applications

Automotive, General Purpose, Sports Equipment

### Regional Availability

North America