

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.011	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Break	11.7	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Shore A Hardness	91	-	ASTM D 2240
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Surface Resistivity	1E12	Ohm	ASTM D 257
Volume Resistivity	1E12	Ohm*cm	ASTM D 257
<b>Other properties</b>			
Density	1030	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Delivery form

Pellets

#### Special Characteristics

Increased electrical conductivity, Anti-static

#### Regional Availability

North America, Europe, Asia Pacific, Near East/Africa