

**THERMOLAST® K TC8CEZ**

TPE

KRAIBURG TPE GmbH &amp; Co. KG

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>18</b>	MPa	ISO 37
Strain at break	<b>580</b>	%	ISO 37
Tear strength	<b>35</b>	kN/m	ISO 34-1
Shore A hardness	<b>80</b>	-	ISO 7619-1

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1200</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>2 - 6</b>	h	-
Injection pressure	<b>20 - 100</b>	MPa	-
Back pressure	<b>2 - 10</b>	MPa	-
Holding pressure	<b>8 - 60</b>	MPa	-
Maximum residence time	<b>10</b>	min	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Black

**Features**

Good Adhesion, Low Fogging, Low Odor, Scratch Resistant, Soft Feel

**Chemical Resistance**

General Chemical Resistance, Grease Resistance, Oil Resistance

**Applications**

Automotive, Packaging

**Regional Availability**

North America, Europe, Asia Pacific