

**Product Texts**

Electrical resistivity: < 10 Ohm cm (ISO 3915)

In-process recycling possible.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>8</b>	MPa	ISO 37
Strain at break	<b>500</b>	%	ISO 37
Tear strength	<b>34.5</b>	kN/m	ISO 34-1
Shore A hardness	<b>83</b>	-	ISO 7619-1

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>990</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>60 - 80</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Melt temperature	<b>200 - 250</b>	°C	-
Mold temperature	<b>25 - 40</b>	°C	-
Zone 1	<b>180</b>	°C	-
Zone 2	<b>200</b>	°C	-
Zone 3	<b>220</b>	°C	-
Injection pressure	<b>20 - 100</b>	MPa	-
Back pressure	<b>2 - 10</b>	MPa	-
Holding pressure	<b>8 - 60</b>	MPa	-
Maximum residence time	<b>10</b>	min	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Black

**Special Characteristics**

Increased electrical conductivity

**Features**

Good Adhesion, Soft Feel

**Applications**

Automotive, Electrical and Electronical, Sports Equipment

**Regional Availability**

North America, Europe, Asia Pacific