

**THERMOLAST® K TF2SNT**

TPE

KRAIBURG TPE GmbH &amp; Co. KG

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>3</b>	MPa	ISO 37
Strain at break	<b>750</b>	%	ISO 37
Tear strength	<b>8</b>	kN/m	ISO 34-1

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1040</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>60 - 80</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Melt temperature	<b>160 - 180</b>	°C	-
Mold temperature	<b>25 - 40</b>	°C	-
Zone 1	<b>140 - 160</b>	°C	-
Zone 2	<b>160 - 180</b>	°C	-
Zone 3	<b>180 - 220</b>	°C	-
Injection pressure	<b>20 - 100</b>	MPa	-
Back pressure	<b>2 - 10</b>	MPa	-
Holding pressure	<b>8 - 60</b>	MPa	-
Maximum residence time	<b>10</b>	min	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Natural Color

**Features**

Good Adhesion, Soft Feel

**Certifications**

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

**Regional Availability**

North America, Europe, Asia Pacific