

**THERMOLAST® K TF6TAA**

TPE

KRAIBURG TPE GmbH &amp; Co. KG

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>19.5</b>	MPa	ISO 37
Strain at break	<b>600</b>	%	ISO 37
Tear strength	<b>47</b>	kN/m	ISO 34-1
Shore A hardness	<b>56</b>	-	ISO 7619-1

<b>Optical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Haze	<b>11</b>	%	ASTM D 1003

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>940</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>60 - 80</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Injection pressure	<b>20 - 100</b>	MPa	-
Back pressure	<b>2 - 10</b>	MPa	-
Holding pressure	<b>8 - 60</b>	MPa	-
Maximum residence time	<b>10</b>	min	-

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Special Characteristics**

Transparent

**Features**

Good Adhesion, Soft Feel

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

Medical, Packaging

**Regional Availability**

North America, Europe, Asia Pacific