

THERMOLAST® K TF7FMA

TPE

KRAIBURG TPE GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	4.5	MPa	ISO 37
Strain at break	480	%	ISO 37
Tear strength	18	kN/m	ISO 34-1
Shore A hardness	67	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	60 - 80	°C	-
Pre-drying - Time	2 - 4	h	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Natural Color

Features

Good Adhesion, Soft Feel

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Applications

Medical, Packaging

Regional Availability

North America, Europe, Asia Pacific