

THERMOLAST® M TM9HET

TPE

KRAIBURG TPE GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	18.5	MPa	ISO 37
Strain at break	750	%	ISO 37
Compression set at 70 °C, 24h	83	%	ISO 815
Compression set at 100 °C, 24h	85	%	ISO 815
Tear strength	73.5	kN/m	ISO 34-1
Shore D hardness	39	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	60 - 80	°C	-
Pre-drying - Time	2 - 4	h	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Transparent, Sterilizable, Ethylene Oxide (EtO) Sterilization, Steam sterilization, Gamma irradiation sterilization

Features

Good Adhesion, Weldable

Chemical Resistance

Radiation Resistance

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR, Medical Grade, Biocompatibility ISO 10993, US Pharmacopeia Class VI Approved, Drug Master File, Long term supply assurance, RoHS compliant, REACH

Applications

Medical

Regional Availability

North America, Europe, Asia Pacific