

THERMOLAST® V TV8LVN

TPE

KRAIBURG TPE GmbH & Co. KG

| Mechanical properties | Value | Unit | Test Standard |
|--------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Tensile Strength | 10 | MPa | ISO 37 |
| Strain at break | 450 | % | ISO 37 |
| Compression set at 70 °C, 24h | 42 | % | ISO 815 |
| Compression set at 100 °C, 24h | 44 | % | ISO 815 |
| Tear strength | 21 | kN/m | ISO 34-1 |
| Shore A hardness | 79 | - | ISO 7619-1 |

| Thermal properties | Value | Unit | Test Standard |
|-------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Burning behav. at thickness h | HB | class | IEC 60695-11-10 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1050 | kg/m ³ | ISO 1183 |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|------------------|-------------|----------------------|
| Pre-drying - Temperature | 60 - 80 | °C | - |
| Pre-drying - Time | 2 - 4 | h | - |
| Melt temperature | 200 - 250 | °C | - |
| Mold temperature | 25 - 40 | °C | - |
| Zone 1 | 180 - 200 | °C | - |
| Zone 2 | 200 - 220 | °C | - |
| Zone 3 | 220 - 250 | °C | - |
| Injection pressure | 20 - 100 | MPa | - |
| Back pressure | 2 - 10 | MPa | - |
| Holding pressure | 8 - 60 | MPa | - |
| Maximum residence time | 10 | min | - |

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Special Characteristics

Heat stabilized or stable to heat

Features

Good Adhesion

Regional Availability

North America, Europe, Asia Pacific