

Volaprint TPE 70 Natur

TPE

Volaprint 3 de-store

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	5.9	MPa	ISO 527
Thermal properties			
ISO Data			
Vicat softening temperature, A	70	°C	ISO 306
Other properties			
Density	1110	kg/m ³	ISO 1183

Characteristics

Processing

Additive Manufacturing

Features

Soft Feel

Delivery form

Monofilament, Natural Color

Regional Availability

Europe