

# Volaprint TPE 75 Transluzent

TPE

Volaprint 3 de-store

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	11	MPa	ISO 527
<b>Thermal properties</b>			
<b>ISO Data</b>			
Vicat softening temperature, A	70	°C	ISO 306
<b>Other properties</b>			
Density	890	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Additive Manufacturing

### Features

Soft Feel

### Delivery form

Monofilament

### Regional Availability

Europe

### Special Characteristics

Translucent