

## Volaprint TPE 90 Natur

TPE

Volaprint 3 de-store

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Yield stress	<b>12.4</b>	MPa	ISO 527
<b>Thermal properties</b>			
<b>ISO Data</b>			
Vicat softening temperature, A	<b>70</b>	°C	ISO 306
<b>Other properties</b>			
Density	<b>1100</b>	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Additive Manufacturing

#### Features

Soft Feel

#### Delivery form

Monofilament, Natural Color

#### Regional Availability

Europe