

Dryflex® Green EP 60A33G1N U

TPO

Hexpol TPE

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Stress at 100% elongation | 2.4 | MPa | ISO 527 |
| Tensile Strength | 4.5 | MPa | ISO 37 |
| Strain at break | 500 | % | ISO 37 |
| Tear strength | 27 | kN/m | ISO 34-1 |
| Shore A hardness | 60 | - | ISO 7619-1 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 870 | kg/m ³ | ISO 1183 |
| Biobased content | 33 | % | - |

Characteristics**Features**

Good Adhesion, Soft Feel

Certifications

Contains renewable resources

Applications

Automotive, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific