

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	14	MPa	ISO 527
Flexural modulus, 23°C	760	MPa	ISO 178
Shore D hardness	56	-	ISO 7619-1
<b>ASTM Data</b>			
Tear Strength	98	kN/m	ASTM D 624

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	131	°C	ISO 75-1/-2
Vicat softening temperature, A	73	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Processing**

Injection Molding

**Applications**

Automotive

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

North America