

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	14	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	19	MPa	ISO 527
Flexural modulus, 23°C	1400	MPa	ISO 178
Charpy notched impact strength, +23°C	50	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	45	kJ/m ²	ISO 180/1A
Izod notched impact strength	4	kJ/m ²	ISO 180/1A
Temperature	-40	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	90	°C	ISO 75-1/-2
Other properties			
Density	1020	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Applications

Automotive

Special Characteristics

High impact or impact modified

Regional Availability

Europe

Features

Copolymer