

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Shore A Hardness	66	-	ASTM D 2240
Tensile Strength at Break	7.79	MPa	ASTM D 412
Elongation at Break	719	%	ASTM D 412
Other properties			
Density	1060	kg/m ³	ASTM D 792

Characteristics

Applications

General Purpose

Regional Availability

North America