

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>3 - 4</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>220 - 250</b>	°C	-
Mold temperature	<b>20 - 40</b>	°C	-

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

U.V. stabilized or stable to weather

**Features**

Good Adhesion, Soft Feel

**Applications**

Automotive, Electrical and Electronical, Sports Equipment

**Regional Availability**

Europe