

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Stress at 100% elongation	1.2	MPa	ISO 527
<sup>[C]</sup> Stress at 300% elongation	1.8	MPa	ISO 527
<sup>[C]</sup> Compression set at 70 °C, 24h	41	%	ISO 815
<sup>[C]</sup> Shore A hardness	55	-	ISO 7619-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	1030	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

## Characteristics

### Delivery form

Natural Color