

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	0.4	MPa	ISO 527
^[C] Stress at 300% elongation	0.7	MPa	ISO 527
^[C] Compression set at 70 °C, 24h	36	%	ISO 815
^[C] Shore A hardness	20	-	ISO 7619-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	880	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form

Natural Color