

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	<b>5.6</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>0.2</b>	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Stress at 100% elongation	<b>0.3</b>	MPa	ISO 527
<sup>[C]</sup> Stress at 300% elongation	<b>0.9</b>	MPa	ISO 527
<sup>[C]</sup> Compression set at 70 °C, 24h	<b>43</b>	%	ISO 815
<sup>[C]</sup> Shore A hardness	<b>17</b>	-	ISO 7619-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	<b>1090</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

## Characteristics

### Delivery form

Black