

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	6.9	MPa	ISO 527
^[C] Stress at 300% elongation	7.7	MPa	ISO 527
^[C] Tear strength	57	kN/m	ISO 34-1
^[C] Shore A hardness	96	-	ISO 7619-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1020	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Natural Color