

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Abrasion resistance	<b>120</b>	mm <sup>3</sup>	ISO 4649
<b>ASTM Data</b>			
Tensile Strength	<b>5</b>	MPa	ASTM D 638
Elongation at Break	<b>500</b>	%	ASTM D 638
Modulus at 100% Elongation	<b>1</b>	MPa	ASTM D 412
Modulus at 300% Elongation	<b>2</b>	MPa	ASTM D 412
Shore A Hardness	<b>48</b>	-	ASTM D 2240
Tear Strength	<b>20</b>	kN/m	ASTM D 624

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1020</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**  
Injection Molding, Other Extrusion

**Chemical Resistance**  
Oil Resistance

**Features**  
Soft Feel

**Regional Availability**  
North America, Europe, Asia Pacific, South and Central America, Near East/Africa