

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Abrasion resistance	<b>30</b>	mm <sup>3</sup>	ISO 4649
<b>ASTM Data</b>			
Tensile Strength	<b>45</b>	MPa	ASTM D 638
Elongation at Break	<b>530</b>	%	ASTM D 638
Flexural Modulus	<b>35</b>	MPa	ASTM D 790
Modulus at 100% Elongation	<b>6.5</b>	MPa	ASTM D 412
Modulus at 300% Elongation	<b>13</b>	MPa	ASTM D 412
Shore A Hardness	<b>89</b>	-	ASTM D 2240
Shore D Hardness	<b>42</b>	-	ASTM D 2240
Tear Strength	<b>105</b>	kN/m	ASTM D 624
Izod Impact notched, Low-Temperature	<b>N</b>	J/m	ASTM D 256
Temperature	<b>-20</b>	°C	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1200</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**  
Injection Molding

**Chemical Resistance**  
Hydrolytically Stable, Oil Resistance

**Special Characteristics**  
Light stabilized or stable to light

**Regional Availability**  
North America, Europe, Asia Pacific, South and Central America, Near East/Africa