

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Abrasion resistance	30	mm ³	ISO 4649
ASTM Data			
Tensile Strength	45	MPa	ASTM D 638
Elongation at Break	450	%	ASTM D 638
Flexural Modulus	205	MPa	ASTM D 790
Modulus at 100% Elongation	19	MPa	ASTM D 412
Modulus at 300% Elongation	33	MPa	ASTM D 412
Shore D Hardness	62	-	ASTM D 2240
Tear Strength	175	kN/m	ASTM D 624
Izod Impact notched, Low-Temperature	115	J/m	ASTM D 256
Temperature	-20	°C	-

Other properties	Value	Unit	Test Standard
Density	1230	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Special Characteristics

Light stabilized or stable to light

Chemical Resistance

Hydrolytically Stable, Oil Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa