

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Abrasion resistance	24	mm ³	ISO 4649
ASTM Data			
Tensile Strength	44.2	MPa	ASTM D 638
Elongation at Break	760	%	ASTM D 638
Modulus at 100% Elongation	7.1	MPa	ASTM D 412
Modulus at 300% Elongation	10.3	MPa	ASTM D 412
Shore A Hardness	90	-	ASTM D 2240
Shore D Hardness	37	-	ASTM D 2240
Tear Strength	102	kN/m	ASTM D 624
Other properties			
Density	1140	kg/m ³	ASTM D 792

Characteristics

Chemical Resistance

Oil Resistance

Certifications

Contains renewable resources

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa