

| Mechanical properties | Value | Unit | Test Standard |
|--------------------------------------|--------------|-----------------|----------------------|
| ISO Data | | | |
| Abrasion resistance | 50 | mm ³ | ISO 4649 |
| ASTM Data | | | |
| Tensile Strength | 40 | MPa | ASTM D 638 |
| Elongation at Break | 600 | % | ASTM D 638 |
| Flexural Modulus | 50 | MPa | ASTM D 790 |
| Modulus at 100% Elongation | 8 | MPa | ASTM D 412 |
| Modulus at 300% Elongation | 18 | MPa | ASTM D 412 |
| Shore A Hardness | 90 | - | ASTM D 2240 |
| Shore D Hardness | 40 | - | ASTM D 2240 |
| Tear Strength | 100 | kN/m | ASTM D 624 |
| Izod Impact notched, Low-Temperature | N | J/m | ASTM D 256 |
| Temperature | -20 | °C | - |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1130 | kg/m ³ | ASTM D 792 |

Characteristics

Processing

Other Extrusion

Chemical Resistance

Hydrolytically Stable, Oil Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa