

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Abrasion resistance	50	mm ³	ISO 4649
ASTM Data			
Tensile Strength	47	MPa	ASTM D 638
Elongation at Break	600	%	ASTM D 638
Modulus at 100% Elongation	6.7	MPa	ASTM D 412
Modulus at 300% Elongation	12.5	MPa	ASTM D 412
Shore A Hardness	90	-	ASTM D 2240
Tear Strength	109	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Characteristics

Processing

Coating

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa