

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Abrasion resistance	55	mm ³	ISO 4649
ASTM Data			
Tensile Strength	15.6	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Modulus at 100% Elongation	4.2	MPa	ASTM D 412
Modulus at 300% Elongation	8.7	MPa	ASTM D 412
Shore A Hardness	80	-	ASTM D 2240
Tear Strength	49	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1030	kg/m ³	ASTM D 792

Characteristics

Processing

Coating

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa