

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	45	MPa	ASTM D 638
Elongation at Break	600	%	ASTM D 638
Modulus at 100% Elongation	5	MPa	ASTM D 412
Modulus at 300% Elongation	10	MPa	ASTM D 412
Shore A Hardness	84	-	ASTM D 2240
Shore D Hardness	34	-	ASTM D 2240
Tear Strength	100	kN/m	ASTM D 624

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	200	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Characteristics

Features

Soft Feel

Chemical Resistance

Hydrolytically Stable

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa