

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>35</b>	MPa	ASTM D 638
Elongation at Break	<b>450</b>	%	ASTM D 638
Modulus at 100% Elongation	<b>11</b>	MPa	ASTM D 412
Modulus at 300% Elongation	<b>20</b>	MPa	ASTM D 412
Shore D Hardness	<b>50</b>	-	ASTM D 2240
Tear Strength	<b>105</b>	kN/m	ASTM D 624

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melting Temperature	<b>175</b>	°C	ASTM D 3418

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1150</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa