

**AVALON® 75 ABX**

TPU

Huntsman Polymers Corp.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>S1</sup></b>			
Tensile Strength	<b>25</b>	MPa	DIN 53504
Strain at break	<b>750</b>	%	DIN 53504
Tear strength	<b>35</b>	kN/m	DIN 53507
Abrasion resistance	<b>50</b>	mm <sup>3</sup>	DIN 53516
Shore A hardness	<b>75</b>	-	DIN 53505

S: These properties are reported by the producer according standards that are different to our defaults.

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>S1</sup></b>			
Density	<b>1140</b>	kg/m <sup>3</sup>	DIN 53479

S: These properties are reported by the producer according standards that are different to our defaults.

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>80 - 90</b>	°C	-
Pre-drying - Time	<b>2</b>	h	-
Mold temperature	<b>25 - 50</b>	°C	-
Feed temperature	<b>25 - 35</b>	°C	-
Zone 1	<b>160 - 180</b>	°C	-
Zone 2	<b>165 - 185</b>	°C	-
Zone 3	<b>165 - 190</b>	°C	-
Nozzle temperature	<b>160 - 185</b>	°C	-
Screw speed	<b>20 - 80</b>	rpm	-
Injection pressure	<b>2 - 10</b>	MPa	-
Back pressure	<b>0.03 - 0.3</b>	MPa	-
Holding pressure	<b>1 - 5</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Features**

Anti Slip, Scratch Resistant

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa