

**Product Texts**

Solution-based polycarbonate urethane.

**Mechanical properties****Value****Unit****Test Standard****ASTM Data**

Tensile Strength	<b>55.2</b>	MPa	ASTM D 638
Elongation at Break	<b>800</b>	%	ASTM D 638

**Characteristics****Processing**

Coating, Casting

**Applications**

Medical

**Chemical Resistance**

Environmental Stress Crack Resistance

**Regional Availability**

North America

**Certifications**

Contains renewable resources, Medical Grade, Biocompatibility  
ISO 10993, US Pharmacopeia Class VI Approved