

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.008	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	220.6	MPa	ASTM D 790
Shore D Hardness	62	-	ASTM D 2240
Tensile Strength at Break	44.5	MPa	ASTM D 412
Elongation at Break	450	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1170	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America